

Test Report No.: 326004375b 001

Page 2 of 5

Material list:

Item: Acoustic Slat Panel

Material No.	Material	Color	Location
M001	Foam + wood	Black/natural	Refer to photo

Test method(s)

- ISO 16000-3:2011 Indoor air – Part 3: Determination of formaldehyde and other carbonyl compounds in indoor air and test chamber air – Active sampling method
- ISO 16000-6:2011 Indoor air – Part 6: Determination of volatile organic compounds in indoor and test chamber air by active sampling on Tenax TA® sorbent, thermal desorption and gas chromatography using MS/FID
- ISO 16000-9:2006 Indoor air – Part 9: Determination of the emission of volatile organic compounds from building products and furnishing – Emission test chamber method

Test chamber conditions

Test chamber:	Corresponding to ISO 16000-9
Test chamber volume:	1 m ³
Temperature of supply air:	23 °C ± 2 °C
Relative humidity of supply air:	50 % ± 5 %
Exchange of air:	0.5 h ⁻¹ ± 0.1 h ⁻¹
Loading factor:	1.0 m ² /m ³
Inflow velocity:	0.2 m/s